

6/2/2006

Product: **N4394**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft ³)	9 - 11	ASTM D-1056
Compressive Resistance – @25%	9 - 13 psi	ASTM D-1056
Tensile Strength (psi)	100	ASTM D-412
Water Absorption % max weight chng	5	ASTM D-1056
Elongation (%)	150	ASTM D-412
Classification	2A3	ASTM D-1056-98
Type/Grade	II-A/B - Medium	MIL R 613 CJUL80
Flammability	pass	UL94 HF-1
Polymer Blend	Neoprene/ EPT/ SBR	

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.