



Technical Data Sheet

1/29/2010

Product: **Durastat**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft ³)	2.8 - 3.1	ASTM D-3574-01
Indent Force Deflection @ 25%	140 - 165	ASTM D-3574-01
Surface Resistance (Ohms/sq)	10 ⁶ - 10 ⁹	ASTM D257
Ohms (point to point)	10 ⁶ - 10 ⁹	
Volume Resistance (Ohms - CM)	10 ⁶ - 10 ⁹	ASTM D257
Static Decay Time (in seconds)	.01 max	
Flame Resistance	N/A	

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

WARNING: URETHANE FOAM IS FLAMMABLE!
Urethane Foam should not be exposed to open flame or other ignition sources.
Urethanes burn rapidly with great heat and release gases which are extremely hazardous.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com