



# Technical Data Sheet

6/2/2006

Product: **7294**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Charcoal Grey	
Density (lbs / ft <sup>3</sup> )	1.75 - 2.10	ASTM D-3574-01
Compression Deflection @ 25% (psi)	0.6 min	ASTM D-3574-01
Tensile Strength (psi)	16 min	ASTM D-3574-01
Elongation (%)	90 min	ASTM D-3574-01
Tear Strength (lbs / lin inch)	1.1 min	ASTM D-3574-01
Flame Resistance	pass pass	FMVSS302 UL94 HF-1

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

**WARNING: URETHANE FOAM IS FLAMMABLE!**  
**Urethane Foam should not be exposed to open flame or other ignition sources.**  
**Urethanes burn rapidly with great heat and release gases which are extremely hazardous.**

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

**[www.amconfoam.com](http://www.amconfoam.com)**